

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : C08G 18/08, 18/72, C09D 175/06	A1	(11) International Publication Number: WO 97/49745 (43) International Publication Date: 31 December 1997 (31.12.97)
(21) International Application Number: PCT/US97/09125 (22) International Filing Date: 28 May 1997 (28.05.97) (30) Priority Data: 08/668,901 24 June 1996 (24.06.96) US (71) Applicant: PPG INDUSTRIES, INC. [US/US]; One PPG Place, Pittsburgh, PA 15272 (US). (72) Inventors: NATESH, Anbazhagan; Apartment 13A3, 700 Lower State Road, North Wales, PA 19454 (US). SWARUP, Shantii; 4918 Meadow Crest Drive, Allison Park, PA 15101 (US). ROSENBERGER, Mary, Ellen; 210 Plymouth Drive, Bay Village, OH 44140 (US). (74) Agents: STACHEL, Kenneth, J.; PPG Industries, Inc., One PPG Place, Pittsburgh, PA 15272 (US) et al.	(81) Designated States: CA, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  Published With international search report.	
(54) Title: AQUEOUS URETHANE RESINS AND COATING COMPOSITIONS HAVING ENHANCED HUMIDITY RESISTANCE (57) Abstract <p>Aqueous dispersions of urethane polymers are disclosed that provide water-based coating compositions with good adhesion following humidity exposure. The polyurethane is made from a first and a second polyisocyanate, the first polyisocyanate having at least one open carbon chain greater than six carbon atoms in length between two isocyanate groups, preferably at least eight carbon atoms in length. The dispersion is particularly useful as a binder resin in coating compositions having pigments that normally have a detrimental effect on adhesion.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

AQUEOUS URETHANE RESINS AND COATING COMPOSITIONS  
HAVING ENHANCED HUMIDITY RESISTANCE

BACKGROUND OF THE INVENTION

5

The present invention relates to aqueous polymer dispersions comprising polyurethanes useful in coating compositions.

In producing water-based polyurethane resins for use in coating compositions, it is desirable to achieve a combination of properties including gloss,  
10 flexibility, durability, abrasion resistance, and solvent resistance. A particular problem encountered with at least some water-based polyurethane coating compositions has been a loss of adhesion when the cured coating is exposed to humid conditions. This problem is particularly troublesome in situations where a waterborne, pigmented basecoat is combined with a solvent-borne topcoat. This is encountered in color-plus-clear automobile coatings.  
15 It would be very desirable to provide aqueous polyurethane basecoat compositions that avoid this problem. Adhesion problems have been found to be exacerbated by some pigments that are used in coating compositions. White pigmented coatings have been found to be particularly susceptible to loss of adhesion following humidity exposure. The following prior art attempts at producing water-based polyurethanes do not address the  
20 humidity resistance problem.

U.S. Patent No. 3,705,164 (Honig et al.) discloses a process for making stable aqueous polymer dispersions by subjecting vinyl monomers (e.g., acrylics) to emulsion polymerization in the presence of a stable aqueous dispersion of a polyurethane containing anionic groups. Coatings are disclosed as a use of the resulting polymer  
25 dispersions.

U.S. Patent No. 4,198,330 (Kaizerman et al.) discloses modifying an aqueous polyurethane by means of vinyl monomers by a process similar to that of the 3,705,164 patent.

U.S. Patent No. 4,644,030 (Loewrigkeit et al.) discloses a method for  
30 making an aqueous dispersion of polyurethane by first producing an isocyanate-terminated polyurethane prepolymer in ethylenically unsaturated monomers such as acrylates. The polyurethane prepolymer is then dispersed in water and is chain-extended. Thereafter the unsaturated monomer material is polymerized *in situ* in the aqueous dispersion.

EP-A-0 308 115 discloses an aqueous polymer dispersion containing an anionic water-dispersible polyurethane and a vinyl polymer obtained by a process similar to that of the 4,644,030 patent.

U.S. Patent No. 4,318,833 (Guagliardo) discloses a waterborne  
5 polyurethane/acrylate in which the acrylate portion is dominant.

U.S. Patent No. 4,791,168 (Salatin et al.) relates to incorporating polyesters made from long-chain carboxylic acids into waterborne polyurethane resins.

U.S. Patent No. 5,118,752 (Chang et al.) discloses aqueous polymerization of vinyl monomers, including acrylates, in the presence of a polymeric surfactant  
10 containing urethane groups and silane groups. Among the isocyanates used to make the urethane portion of the surfactant is included a hydrophobic isocyanate ("DDI")

~~disclosed. A comparative example without silane groups is also disclosed, but is~~  
reported in the patent to perform poorly. All of the examples disclosed in the patent  
employ a substantially larger amount of vinyl polymer relative to the polyurethane polymer,  
15 and the vinyl portion is predominately styrene.

U.S. Patent No. 5,173,526 (Vijayendran et al.) involves a method for making aqueous polyurethane/acrylates similar to Chang et al., except that no silane groups are included, no hydrophobic isocyanates are used, and the use of an oil-soluble initiator is required. The resulting aqueous polymer dispersion is intended for use in paper coatings.

20 Subject matter related to that of the present application is disclosed and claimed in co-pending, commonly owned U.S. Patent Application Serial No. 08/668,069 titled "Humidity Resistant Aqueous Urethane/Acrylic Resins and Coating Compositions" filed on even date herewith by Anbazhagan Natesh, Shanti Swarup, Mary E. Rosenberger, Mary S. Eifert, Karl F. Schimmel, and John W. Burgman.

25

#### SUMMARY OF THE INVENTION

It has now been found that aqueous dispersions of urethane polymers can be made that provide water-based coating compositions with good humidity resistance as well as a combination of performance properties required for commercial coating uses. Coatings  
30 in which the film-forming resin includes the urethane dispersion of the present invention have been found to possess superior adhesion properties. These adhesion properties have been found to be particularly advantageous in certain pigmented coating compositions, particularly white pigmented coatings. Characterizing the polyurethane of the present invention is the selection of polyisocyanates from which it is synthesized. A first

polyisocyanate is characterized by at least one open carbon chain greater than six carbon atoms in length, preferably at least eight carbon atoms in length, between two isocyanate groups. For the sake of reduced cost and providing a range of coating properties, this first polyisocyanate may be combined with one or more different polyisocyanates selected from the more conventional types of polyisocyanates that are used for coatings. Therefore, the first polyisocyanate preferably constitutes a minor portion of the polyisocyanate mixture, e.g., 20% to 50% by weight of the polyisocyanate mixture, although greater amounts are not precluded. The best resistance to water in the cured coatings have been found in embodiments in which the first polyisocyanate constituted at least 25% of the polyisocyanate mixture, preferably at least 30%.

The first polyisocyanate, at least one additional polyisocyanate, an active hydrogen containing compound (e.g., a polyol), and an isocyanate-reactive compound containing a salt-forming group are reacted to form a polyurethane prepolymer, which is then neutralized, dispersed in water, and chain-extended. The first polyisocyanate preferably constitutes at least about 10 weight percent of all the monomers used to make the polyurethane.

The aqueous polyurethane dispersions can be formulated into coating compositions that can be applied to metal substrates, as well as to temperature sensitive substrates such as plastics and wood because curing of the coating can take place at ambient temperatures. Optionally, thermally activated crosslinking agents may be included. The coatings have found utility in the original manufacture of automobiles, low temperature refinish coating of automobiles, and low temperature coating of plastic articles.

The coating composition of the present invention is particularly useful as a pigmented waterborne basecoat to which is applied a clear topcoat, such as a two-component isocyanate coating. When the clear top coat is based on organic solvent-borne resins, the susceptibility of a waterborne basecoat to deterioration of adhesion due to humidity exposure is particularly critical, and the composition of the present invention is particularly adapted to resist such deterioration. This advantage has been found even with pigments such as titanium dioxide that were previously found to have a negative effect on adhesion.

#### DETAILED DESCRIPTION OF THE INVENTION


The aqueous polyurethane dispersion of the present invention may be prepared by forming an isocyanate-terminated polyurethane prepolymer including salt-

forming groups sufficient to permit dispersion of the prepolymer in water, adding a neutralizing agent to the prepolymer to salify the ion-forming groups, dispersing the prepolymer in water, adding a chain extender to the aqueous dispersion, and completing the chain extension of the polyurethane prepolymer.

- 5 The polyurethane prepolymers may be produced by reacting organic material containing an average of at least about two active hydrogen atoms per molecule (usually a diol, typically a polyester polyol) with a stoichiometric excess of a polyisocyanate mixture. Additionally, the reactants for forming the prepolymer include an additional monomer reactive with isocyanate and having a salt-forming group for providing water  
10 dispersibility to the prepolymer.

To attain the results of the present invention, it is important that the polyisocyanate prepolymer be made from at least one polyisocyanate having at least one

- at least C<sub>8</sub> in length. This first isocyanate may additionally include aliphatic, cycloaliphatic,  
15 araliphatic or aromatic segments. It is believed that the presence of the alkylene group contributes to the improved humidity resistance exhibited by the coatings of the present invention. A particular type of polyisocyanate of this type that has been found suitable for use as the first polyisocyanate is characterized by the structure:



20

- where R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, and R<sup>4</sup> may be the same or different, R<sup>1</sup> and R<sup>2</sup> each contain alkylene groups greater than C<sub>6</sub> in length (preferably at least C<sub>8</sub>), and R<sup>3</sup> and R<sup>4</sup> each are H or an alkyl group. Preferably both of R<sup>3</sup> and R<sup>4</sup> are alkyl groups. In general, longer alkyl or  
25 alkylene groups provide greater hydrophobicity to the prepolymer, which is desirable. Although no upper limit has been identified, appropriate compounds having alkylene groups longer than C<sub>20</sub> are uncommon. An example of such a polyisocyanate is "DDI® 1410" diisocyanate available from the Henkel Corporation, which is 2-heptyl-3,4-bis(9-isocyanatononyl)-1-pentyl-cyclohexane.

- 30 Although polyisocyanates of the above-described first type may theoretically be used for the entire isocyanate content of the prepolymer, practical considerations such as cost generally limit them to no more than 50 percent by weight of the

isocyanate monomer content. Providing a second polyisocyanate also permits additional attributes to be imparted to the product. In the particular embodiments tested, the advantages of the present invention were not perceptible when the first polyisocyanate was used in amounts less than about 20 percent by weight of the total polyisocyanate mixture.

- 5 Significant improvements may be obtained when the first polyisocyanate constitutes at least 25 percent of the polyisocyanate mixture, and optimum results were obtained at levels of at least 30 percent. The remainder of the polyisocyanate mixture may constitute a second polyisocyanate of a more conventional type.


- Polyisocyanates that may be used as the second polyisocyanate in making  
10 the prepolymer may be selected from a wide range of polyisocyanate compounds considered suitable for coating applications. These include aliphatic, cycloaliphatic, araliphatic or aromatic polyisocyanates. Examples of suitable polyisocyanates include ethylene diisocyanate, 1,6-hexamethylene diisocyanate, isophorone diisocyanate, cyclohexane-1,4-diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, 1,4-phenylene  
15 diisocyanate, 2,4-toluene diisocyanate, 2,6-toluene diisocyanate, 4,4'-diphenylmethane diisocyanate, 2,4'-diphenylmethane diisocyanate, polymethylene polyphenyl polyisocyanates and 1,5-naphthylene diisocyanate. The second isocyanate may also include mixtures of polyisocyanates.

- The polyol component reacted with the polyisocyanates to form the  
20 polyurethane prepolymer may be members of any of the chemical classes of polymeric polyols used or proposed to be used in polyurethane formulations. Low molecular weight diols could possibly be used, but it is preferred to use polymeric polyols for at least a portion of the polyol component for the sake of flexibility in the coating. Polymeric polyols having molecular weights in the range of 200-6000 are typical. In particular, the polyols  
25 may be polyesters, polyesteramides, polyethers, polythioethers, polycarbonates, polyacetals, polyolefins or polysiloxanes. Polyester polyols are particularly preferred and include hydroxyl-terminated reaction products of polyhydric alcohols such as ethylene glycol, propylene glycol, diethylene glycol, neopentyl glycol, 1,4-butanediol, furan dimethanol, cyclohexane dimethanol, glycerol, trimethylolpropane or pentaerythritol, or  
30 mixtures thereof, with polycarboxylic acids, especially dicarboxylic acids or their ester-forming derivatives, for example succinic, glutaric, and adipic acids or their methyl esters, phthalic anhydride, or dimethyl terephthalate. Polyesters obtained by the polymerization of lactones, for example caprolactone, in conjunction with the polyol may also be used.

Polyesteramides may be obtained by the inclusion of amino-alcohols such as ethanolamine in the polyesterification mixtures.

To provide for water dispersibility, the monomer mixture used to produce the polyurethane prepolymer may include isocyanate-reactive compounds containing salt forming groups. Most conveniently, the polymer is made anionic, whereby the salt-forming group may be a carboxylic acid group which can subsequently be neutralized to salt form. In that case, the monomer can be a polyol having a carboxylic acid group. These include carboxy group containing diols and triols, for example dihydroxyalkanoic acids of the formula

10



wherein R is hydrogen or a C<sub>1</sub>-C<sub>10</sub> alkyl group. Specific examples of isocyanate-reactive acids include 2,2-di(hydroxymethyl)acetic acid, 2,2,2-tri(hydroxymethyl)acetic acid, 2,2-di(hydroxymethyl)butyric acid, 2,2-di(hydroxymethyl)pentanoic acid, and the like. The preferred carboxy-containing diol is 2,2-di(hydroxymethyl)propionic acid. If desired, the carboxy-containing diol or triol may be incorporated into a polyester by reaction with a dicarboxylic acid before being incorporated into the prepolymer. The concentration of salt-forming groups is chosen so as to provide stability to the aqueous dispersion of the prepolymer in water. This will vary in accordance with the hydrophobicity of the particular polymer. For the best results, the acid number for the final polyurethane dispersion may be in the range of 1 to 125 milligrams KOH per gram of polymer solids, preferably 5 to 100.

The anionic, water-dispersible, isocyanate-terminated polyurethane prepolymer may be prepared in conventional manner by reacting a stoichiometric excess of the polyisocyanates with the polymeric polyols under substantially anhydrous conditions at a temperature between about 30°C and 130°C until the reaction between the isocyanate groups and the hydroxyl groups is substantially complete. The polyisocyanate and the polyol components are suitably reacted in such proportions that the ratio of number of isocyanate groups to the number of hydroxyl groups is in the range from about 1.1:1 to about 6:1, preferably within the range of from 1.5:1 to 3:1. If desired, the well-known tin catalysts may be used to assist prepolymer formation.



Before the prepolymer is dispersed in water, ammonia or a water soluble or dispersible amine is added to the mixture in an amount sufficient to substantially neutralize the carboxylic functionality as is well known in the art. The amine is added at about 65 to 120% amine equivalent per equivalent of carboxy functionality, preferably about 80% to 100%. Amines that may be used for neutralization are relatively volatile so that they may evaporate from the coating upon curing. Ammonia, or primary, secondary, or tertiary aliphatic, alicyclic, aromatic, araliphatic or heterocyclic amines may be used. Amines with hydroxy substituted alkyl groups may also be suitable. Examples of amines include diethylamine, diethanolamine, diisopropanolamine, 2-methyl-2-aminopropanol, triethylamine, dimethylethanolamine, methyldiethanolamine, and methyldiethylamine. The prepolymer/vinyl monomer mixture may be dispersed in water using techniques well known in the art. Preferably, the mixture is added to the water with agitation, or, alternatively, water may be stirred into the mixture.

The polyurethane prepolymer is preferably chain extended by addition of an active hydrogen-containing compound to the aqueous system. The chain extender may be a polyol, an amino alcohol, ammonia, or a primary or a secondary aliphatic, alicyclic, aromatic, araliphatic or heterocyclic amine, especially a diamine. Examples of suitable chain extenders include ethylenediamine, diethylene triamine, triethylene tetramine, propylene diamine, butylene diamine, pentane diamine, hexamethylene diamine, cyclohexylene diamine, piperazine, 2-methyl piperazine, phenylene diamine, toluene diamine, tris(2-aminoethyl)amine, 4,4'-methylenebis(2-chloraniline), 3,3'-dichloro-4,4'-diphenyl diamine, 2,6-diaminopyridine, 4,4'-diaminodiphenyl methane, isophorone diamine, and adducts of diethylenetriamine with acrylate or its hydrolyzed products. Also suitable are amines as above having substitutions in the alkyl groups.

The amount of chain extender employed should be approximately equivalent to the free isocyanate groups in the prepolymer, the ratio of active hydrogens in the chain extender to isocyanate groups in the prepolymer preferably being in the range from 0.7 to 1.3:1. When water is employed as the chain extender, these ratios will not be applicable since the water, functioning as both a chain extender and dispersing medium, will be present in a gross excess relative to the free isocyanate groups. The chain extending reaction begins to proceed upon addition of the chain extender to the aqueous dispersion.

The polymer dispersions obtained typically comprise 20 to 60 weight percent solids and may be employed as coating compositions and applied to any substrate including metals, plastics glass, wood, cloth, leather, paper, foam and the like by any

conventional method including brushing, dipping, flow coating, spraying and the like. Generally, a coating of the aqueous composition is dried and cured at temperatures ranging from ambient to about 150°C for times ranging from 24 hours to 30 minutes. This is advantageous for use on plastics and for refinish coating of automobiles. Alternatively, any of the thermally activated crosslinking agents commonly used for coatings, such as the many commercially available aminoplast resins (e.g., alkoxylated melamine derivatives), may be included in the coating compositions. These coating compositions of the present invention that include a crosslinking agent may be cured at elevated temperatures. Embodiments that include crosslinking agents are preferred for original automobile manufacturing applications. Other crosslinking mechanisms, such as the silane functionality required by U.S. Patent No. 5,118,752 (Chang et al.), are not required in the present invention, and are preferably avoided in order to obtain the humidity resistance found in the

invention is preferably substantially free of silane groups.

#### EXAMPLE 1

An aqueous polyurethane polymeric dispersion in accordance with the present invention was made using the ingredients as follows:

Feed	Ingredient	Parts by weight
1.	Methylene dicyclohexyl diisocyanate <sup>1</sup>	340.0
2.	DDI <sup>®</sup> 1410 diisocyanate <sup>2</sup>	197.2
25 3.	FORMREZ <sup>®</sup> 66-56 <sup>3</sup>	546.6
4.	Dibutyltin dilaurate	0.96
5.	Dimethylol propionic acid	72.0
6.	Methyl isobutyl ketone	266.2
7.	Neopentyl glycol	12.0
30 8.	Triethyl amine	54.3
9.	Ethylene diamine	34.2
10.	Deionized water	3260.2

<sup>1</sup> DESMODUR® W from Bayer Corp., Pittsburgh, Pennsylvania.

<sup>2</sup> 2-heptyl-3,4-bis(9-isocyanato nonyl)-1-pentyl-cyclohexane from Henkel Corporation.

<sup>3</sup> Poly(1,6-hexanediol adipate), molecular weight about 2000, from Witco Corporation.

5

Into a clean dry reactor equipped with heating, cooling, stirring and a nitrogen blanket were charged feeds 1 to 7. The reaction mixture was heated to 75°C and brought to equilibrium. The temperature was then raised to about 97°C and held at this temperature for 2 hours. After this hold, the temperature was reduced to 65°C and feed 8 was added. The prepolymer/monomer mixture was then transferred into another reactor containing feeds 9 and 10. The resulting dispersion was heated to 40°C, and held for one hour. The product thus formed had the following physical properties: total solids of 26.6% and acid value of 7.3.

15

#### EXAMPLE 2

Although not required by the present invention, a preferred coating composition embodying the present invention may include, for the sake of additional property enhancements, an additive component comprising a cellulose acetate butyrate/acrylic dispersion, the preparation of which is described in this example. This material is the subject matter of co-pending, commonly owned U.S. Patent Application Serial No. 08/669,815 titled "Stable Aqueous Dispersions of Cellulose Esters, Method of Making and Their Use in Coatings" filed on even date herewith by Suryya K. Das et al.

A pre-emulsion of cellulose acetate butyrate and acrylic monomer mixture was prepared by dissolving 158.0 grams of cellulose acetate butyrate (CAB-551-0.01, available from Eastman Chemical Co., USA) in 577.8 grams of n-butyl acrylate by stirring at room temperature. Acrylic monomers (22.1 grams of 2-hydroxyethyl methacrylate, 18.9 grams of ethylene glycol dimethacrylate and 12.6 grams of acrylic acid) were added and the mixture was agitated for about 20 minutes before adding 14.8 grams of ALIPAL CO-436 anionic surfactant (ammonium salt of ethoxylated nonylphenol sulfate, from Rhone-Poulenc). After mixing for 10 minutes, 1000.0 grams of deionized water and 3 drops of FOAMKILL 649 defoamer (from Crucible Chemicals, Greenville, South Carolina) were added and stirred for about 5 minutes for pre-emulsification.

The pre-emulsion was passed once through a M110T Microfluidizer<sup>®</sup> emulsifier at 8000 psi to produce a microdispersion. While stirring the microdispersion at room temperature in a round bottom flask, a mixture of 1.34 grams of 1 percent aqueous solution of ferrous ammonium sulfate and 16.6 grams of deionized water was added the  
5 mixture, and the mixture was then heated to 40°C under nitrogen. A solution of 2.6 grams of isoascorbic acid in 33.4 grams of deionized water was added rapidly and followed by the addition of the following solution over 10 minutes:

	Ingredients	Parts by weight
10	ALIPAL CO-436	7.4
	Deionized water	154.6
	Tert-butylhydroperoxide (70 percent active in water)	3.6

The temperature rose spontaneously to 92°C. The product was filtered to yield a latex with  
15 a resin content of 38.9 percent determined at 110°C for one hour and a pH of 2.79. The pH of the latex was adjusted to 8.33 using 11.0 grams of N,N-dimethylethanolamine as a neutralizing agent.

### EXAMPLE 3

20 The following is a white pigmented aqueous coating composition in accordance with the present invention employing the polyurethane dispersion of Example 1 and the additive of Example 2.

---

25	Ingredient	Parts by weight
	1. Butyl CELLOSOLVE <sup>®</sup> <sup>1</sup>	37
	2. Hexyl CELLOSOLVE <sup>®</sup> <sup>2</sup>	4
	3. Polypropylene glycol <sup>3</sup>	2.5
30	4. Deionized water	72
	5. Thickener <sup>4</sup> 1:1 aqueous solution	3
	6. Acid functional acrylic grind vehicle	32
	7. UV control package <sup>5</sup>	11
	8. RESIMENE <sup>®</sup> 750 cross-linking agent <sup>6</sup>	20

	9. TiO <sub>2</sub> pigment in acrylic paste	324
	10. Black pigment <sup>7</sup>	2
	11. Yellow pigment <sup>8</sup>	2.5
	12. Triethyl amine	2
5	13. CAB dispersion of Example 2	184
	14. Polyurethane dispersant of Example 1	111
	15. Mineral spirits	41

<sup>1</sup> Ethylene glycol butyl ether solvent from Union Carbide Chemicals and Plastics Co.

10 <sup>2</sup> Ethylene glycol hexyl ether solvent from Union Carbide Chemicals and Plastics Co.

<sup>3</sup> Molecular weight approximately 425, from Arco Chemicals.

<sup>4</sup> Thickener sold by Imperial Chemical Industries under the name "ASE-68."

<sup>5</sup> UV control package includes combination of: CYAGARD 711 and CYAGARD 1790, both antioxidants from Cytec Technology Corp.; SANDUVOR 3058 UV absorber from

15 Clariant Industries; and CYASORB 1164 UV absorber from Cytec Technology Corp.

<sup>6</sup> Melamine derivative from Monsanto Chemical Co.

<sup>7</sup> Black pigment from Cabot Corporation.

<sup>8</sup> Yellow pigment from Columbian Chemical Co.


20 Ingredients 1 through 12 constitute a pigment paste that was prepared separately in a conventional pigment milling operation. The paste was then let down by addition of ingredients 13 through 15. The resulting coating composition was tested for performance by spray application onto steel panels previously coated with a primer coating. The panels were baked for 35 minutes at 146°C and tested for adhesion and chip resistance.

25 The cured films were evaluated for humidity resistance and were found to have good humidity resistance properties. The cured films of this example were also tested for resistance to chipping due to stone impact, and were found to have excellent resistance. Therefore, this composition met very high standards for automobile manufacturers.

30 Although certain embodiments of the invention have been described in detail for the purpose of illustrating the best mode of the invention, it is to be understood that such detail is solely for that purpose and that variations can be made by those skilled in the art without departing from the spirit and scope of the invention as defined by the claims.

## CLAIMS:

1. A water reducible polyurethane resin which comprises the reaction product of:
- 5 (i) a first polyisocyanate having an open carbon chain greater than  $C_6$  in length between two isocyanate groups;
- (ii) a second isocyanate different from the first polyisocyanate;
- (iii) a polyol; and
- (iv) a monomer having an anionic group and functionality reactive with
- 10 isocyanate;
2. The resin of claim 1 wherein the polyurethane is the reaction product of:
- (ii) 15 - 50 percent by weight of said second isocyanate;
- 15 (iii) 25 - 70 percent by weight of said polyol; and
- (iv) 1 - 10 percent by weight of said monomer having an anionic group and functionality reactive with isocyanate;
- the weight percentages based on total resin solids weight of the polyurethane reactants.
- 20 3. The resin of claim 1 wherein the polyurethane is the reaction product of:
- (i) 10 - 20 percent by weight of said first polyisocyanate;
- (ii) 20 - 40 percent by weight of said second isocyanate;
- (iii) 40 - 60 percent by weight of said polyol; and
- 25 (iv) 5 - 10 percent by weight of said monomer having an anionic group and functionality reactive with isocyanate;
- the weight percentages based on total resin solids weight of the polyurethane reactants.
- 30 4. The resin of claim 1 where said first polyisocyanate has the structure



where  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  may be the same or different,  $R^1$  and  $R^2$  each contain alkylene groups greater than  $C_6$  in length, and  $R^3$  and  $R^4$  each are H or an alkyl group.

5      5. The resin of claim 4 wherein  $R^1$  and  $R^2$  each contain alkylene groups at least  $C_8$  in length, and  $R^3$  and  $R^4$  each are an alkyl group.

6. A coating composition comprising:

(a) a water reducible polyurethane resin comprising the reaction product of:

10      (i) a first polyisocyanate having an open carbon chain greater than  $C_6$  in length between two isocyanate groups;

(ii) a second isocyanate different from the first polyisocyanate;

(iii) a polyol; and

(iv) a monomer having an anionic group and functionality reactive with isocyanate;

15      (b) pigment; and

(c) water.

7. The coating composition of claim 6 wherein the pigment comprises titanium dioxide.

## INTERNATIONAL SEARCH REPORT

Internal Application No

PCT/US 97/09125

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C08G18/08 C08G18/72 C09D175/06

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C08G C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

### C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
------------	--	-----------------------

June 1992  
cited in the application  
see column 1, line 18 - line 32  
see column 3, line 26 - column 5, line 52  
see examples 1,2,7

A US 5 268 397 A (LARSON DONALD B) 7  
December 1993  
see column 3, line 44 - column 7, line 52  
see example 32

A US 5 086 110 A (XIAO HAN X ET AL) 4  
February 1992  
see column 1, line 22 - column 2, line 27  
see examples 1-4  
see claims 1-2

### 1.4.5

1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\* & document member of the same patent family

Date of the actual completion of the international search

20 August 1997

Date of mailing of the international search report

15.09.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax (+31-70) 340-3016

Authorized officer

Neugebauer, U

Form PCT/ISA/210 (second sheet) (July 1992)

page 1 of 2



# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 97/09125

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 4 203 883 A (HANGAUER DAVID G JR) 20 May 1980 see column 2, line 43 - column 6, line 30 see column 7, line 47 - column 9, line 39 see example 1 see claim 1</p> <p>-----</p>	1

1

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

page 2 of 2

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 97/09125

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5118752 A	02-06-92	AT 146796 T CA 2121265 A DE 69216249 D DE 69216249 T EP 0608274 A ES 2098541 T JP 6510559 T WO 9308218 A	15-01-97 29-04-93 06-02-97 17-07-97 03-08-94 01-05-97 24-11-94 29-04-93
US 5268397 A	07-12-93	NONE	
US 5086110 A	04-02-92	NONE	
US 4203883 A	20-05-80	CA 1131376 A AU 515721 B AU 2934377 A DE 2744544 A FR 2366319 A GB 1575637 A	07-09-82 30-04-81 12-04-79 06-04-78 28-04-78 24-09-80 24-04-78
		NL 7710827 A,B,	06-04-78

Form PCT/ISA/210 (patent family annex) (July 1992)